Filita



JAPAN CERAMICS

26 Daisy Street
Revesby NSW 2212
P 02 9772 2088
E sales@japanceramics.com.au
japanceramics.com.au

FILITA

COLOURS, FORMATS & FINISHES



Textured | P5

Filita

440 x 660mm Flagstone	●

FINISH: **TEXTURED** | CATEGORY: PORCELAIN TILES | EDGE DETAIL: UNRECTIFIED | V RATING: V2



Filita





440 x 660mm
FILFL46 (textured)



JAPAN CERAMICS

Technical Specifications

Properties	Test Method	Required Value	Value	Applies to
Water absorption	ISO 10545-3	⩽ 0.5%	⩽ 0.10%	Full range
Determination of dimensions	ISO 10545-2	Length and width 0.6% Thickness 0.5% Edge straightness 0.5% Surface flatness 0.5%	Complies with standards	Full range
Breaking strength	ISO 10545-4	⩾ 1300 N	Complies with standards	Full range
Abrasion resistance	ISO 10545-6	Max 175mm3	Complies with standards	Full range
Slip resistance (wet pendulum test)	Wet Pendulum Test	N/A	P5	Textured
Slip resistance (oil wet ramp test)	DIN 51130	N/A	R12	Full range
Chemical resistance	ISO 10545-13	Minimum UB	Complies with standards	Full range
Stain resistance	N/A	N/A	N/A	Full range
Origin	N/A	N/A	Spain	Full range
Shade variation	N/A	N/A	V3	Full range



JAPAN CERAMICS

Packing Information

Tile Description		Quantity per Box	Quantity per m2		Quantity per Pallet	
Size (mm)	Finish	Pieces	Pieces	Weight	m2	Boxes
440 x 660 Flagstone	Textured	4	3.42	24.00kg	56.16	48



The data and information contained in these specification sheets are indicative only unless stated otherwise. As Japan Ceramics cannot control the conditions under which these products are manufactured, the specifications supplied should be considered as suggested guidelines only and are subject to batch variation. The information contained in these specification sheets should not be considered a warranty, expressed or implied, including, but not limited to, a warranty of merchantability or fitness for a particular purpose. To the maximum extent permitted by law, ColorTile will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given in respect of any specification provided herein other than those that cannot be excluded under the Australian Consumer Law.

JAPAN CERAMICS

IMPORTANT NOTE:
Slip ratings are indicative only. Actual performance may vary depending on installation, surface conditions, and maintenance.

Slip Check to AS 4586-2013

Filita Flagstone

Report Number: R28746
Report Date: 15 May 2023
Total Number of Pages 2

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Limited

Issued by	Prepared for	Approved by
Safe Environments Pty Limited Unit 4, 40 Bessemer Street Blacktown NSW 2148	Japan Ceramics 26 Daisy Street Revesby NSW 2212	Dylan Anderson Authorised Signatory

SlipCheck
CREATING SAFE ENVIRONMENTS
www.FloorSlipTest.com.au

Unit 4/40 Bessemer St
Blacktown NSW 2148
Phone 02 9621 3706
info@SafeEnvironments.com.au

15 May 2023

Test Report No. R28746

Slip Resistance ClassificationofNewPedestrianSurface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by:	Japan Ceramics
Client Address:	26 Daisy Street Revesby NSW 2212
Product Manufacturer:	Realonda Ceramica
Product Description:	Filita Flagstone
Test conducted according to:	AS 4586:2013 Appendix A
Sampling Procedures:	Performed by client and tested as received.
Location:	4/40 Bessemer Street, Blacktown NSW 2148
Conducted by:	Yuliana Vargolomova
Date:	11 May 2023
Sample:	Unfixed
Rubber slider used:	Slider 96
Slope of specimen:	Tested on a flat level surface
Direction of Test:	NA
Temperature:	18 C
Cleaning:	None
Conditioned:	Grade P 400 paper dry followed by wet lapping film

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	70	64	72	74	66

Reported SRV of Sample:	**69**
Class:	**P5**

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8%, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.

This test report shall not be reproduced unless in full, without written approval of Safe EnvironmentsPtyLtd