Miyako



JAPAN CERAMICS

26 Daisy Street
Revesby NSW 2212
P 02 9772 2088
E sales@japanceramics.com.au
japanceramics.com.au

MIYAKO

COLOURS, FORMATS & FINISHES


Matt | P3



Chalk White


Coast


Amber Brown


Ether


Forest


Volcanic

50 x 150mm	●	●	●	●	●	●
100 x 150mm	●	●	●	●	●	●


Gloss



White


Morchella


Pura


Coffee


Golden Orche


Oil Blue



Blue Moon


Crystal Pink

50 x 150mm	●	●	●	●	●	●	●	●

FINISH: **MATT** | CATEGORY: PORCELAIN TILES | EDGE DETAIL: RECTIFIED | V RATING: V4
FINISH: **GLOSS** | CATEGORY: PORCELAIN TILES | EDGE DETAIL: RECTIFIED | V RATING: V2







100 x 150mm
MIYCW115M (matt)



50 x 150mm
MIYCW515M (matt)






100 x 150mm
MIYCO115M (matt)



50 x 150mm
MIYCO515M (matt)

JAPAN CERAMICS





100 x 150mm
MIYAM115M (matt)



50 x 150mm
MIYAM515M (matt)






100 x 150mm
MIYET115M (matt)




50 x 150mm
MIYET515M (matt)

JAPAN CERAMICS






100 x 150mm
MIYFO115M (matt)




50 x 150mm
MIYFO515M (matt)





100 x 150mm
MIYVO115M (matt)




50 x 150mm
MIYVO515M (matt)

JAPAN CERAMICS





50 x 150mm
MIYWH515 (gloss wall)






50 x 150mm
MIYMO515 (gloss wall)

JAPAN CERAMICS






50 x 150mm
MIYPU515





50 x 150mm
MIYCF515 (gloss wall)


JAPAN CERAMICS





50 x 150mm
MIYGO515 (gloss wall)





50 x 150mm
MIYOB515 (gloss wall)

JAPAN CERAMICS





50 x 150mm
MIYBM515 (gloss wall)





50 x 150mm
MIYCP515 (gloss wall)

JAPAN CERAMICS

Technical Specifications

Properties	Test Method	Required Value	Value	Applies to
Water absorption	ISO 10545-3	⩽ 0.5%	> 0.5%	Full range
Determination of dimensions	ISO 10545-2	Length and width ± 0.75% Thickness ± 5.00%	Length and width ± 0.5% Thickness ± 10%	Full range
Breaking strength	ISO 10545-4	⩾ 1300N	> 1300N	Full range
Modulus of rupture	ISO 10545-4	⩾ 35 N/mm2	⩾ 35 N/mm2	Full range
Abrasion resistance	ISO 10545-6	Class 3 min	Class 3	Full range
Slip resistance (wet pendulum test)	AS 4459.14-1999	N/A	P3 - Matt	Matt
Chemical resistance	ISO 10545-13	GB min.	GLA, GHB, GA	All finishes
Stain resistance	ISO 10545-14	Class 3 min.	Class 5	Full range
Origin	N/A	N/A	Spain	Full range
Shade variation	N/A	N/A	V4	Full range



JAPAN CERAMICS

Packing Information

Tile Description		Quantity per Box	Quantity per m2		Quantity per Pallet	
Size (mm)	Finish	Pieces	Pieces	Weight	m2	Boxes
50 x 150	Matt Gloss	66	133.33	17.27kg	59.40	120
100 x 150	Matt	40	66.67	17.33kg	57.60	96



The data and information contained in these specification sheets are indicative only unless stated otherwise. As Japan Ceramics cannot control the conditions under which these products are manufactured, the specifications supplied should be considered as suggested guidelines only and are subject to batch variation. The information contained in these specification sheets should not be considered a warranty, expressed or implied, including, but not limited to, a warranty of merchantability or fitness for a particular purpose. To the maximum extent permitted by law, ColorTile will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given in respect of any specification provided herein other than those that cannot be excluded under the Australian Consumer Law.

JAPAN CERAMICS

IMPORTANT NOTE:
Slip ratings are indicative only. Actual performance may vary depending on installation, surface conditions, and maintenance.

Slip Check to AS 4586-2013

Miyako Matt 100x150

Report Number: R35203
Report Date: 17 February 2026
Total Number of Pages 2

Safe Environments quality management system is certified to ISO 9001:2015

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Limited

Issued by	Prepared for	Approved by
Safe Environments Pty Limited 6/7 Inglewood Place Norwest NSW 2153	Japan Ceramics Pty Ltd 26 Daisy Street Revesby NSW 2212	Mathew Sutton Authorised Signatory

SlipCheck
CREATING SAFE ENVIRONMENTS
www.FloorSlipTest.com.au

6/7 Inglewood Place
Norwest NSW 2153
Phone02 9621 3706
info@SafeEnvironments.com.au

17 February 2026

Test Report No. R35203

Slip Resistance ClassificationofNewPedestrianSurface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by:	Japan Ceramics Pty Ltd
Client Address:	26 Daisy Street Revesby NSW 2212
Product Manufacturer:	Equipe Ceramics
Product Description:	Miyako Matt 100x150
Test conducted according to:	AS 4586:2013 Appendix A
Sampling Procedures:	Performed by client and tested as received.
Location:	6/7 Inglewood Place, Norwest NSW 2153
Conducted by:	Liam Kennelly

Date:	17 February 2026	Temperature:	25°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	N/A		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	45	45	40	45	45

Reported SRV of Sample:	**44**
Class:	**P3**

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8%, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.

This test report shall not be reproduced unless in full, without written approval of Safe EnvironmentsPtyLtd