Panama



JAPAN CERAMICS

26 Daisy Street
Revesby NSW 2212
P 02 9772 2088
E sales@japanceramics.com.au
japanceramics.com.au

PANAMA

COLOURS, FORMATS & FINISHES



In/Out | P4	Ivory	Natural	Grey
600 x 1200mm	●	●	●
600 x 1200mm Linear	●	●	●
600 x 600mm	●	●	●
300 x 600mm	●	●	●

Textured | P5			
600 x 600mm 20mm Paver	●	●	●
398 x 600mm Coping Paver	●	●	●

FINISH: **IN**/**OUT** | CATEGORY: PORCELAIN TILES | EDGE DETAIL: RECTIFIED | V RATING: V2

FINISH: **TEXTURED** | CATEGORY: PORCELAIN TILES | EDGE DETAIL: RECTIFIED | V RATING: V2





600 x 600mm
PANIV60 (in/out)
PANIV60-20 (textured 2CM)

600 x 1200mm
PANIV612 (in/out)
PANIV612 (linear in/out)

398 x 600mm Coping Paver
PANIV46-20L (textured 2CM)

300 x 600mm
PANIV36 (in/out)



600 x 600mm
PANNAT60 (in/out)
PANNAT60-20 (textured 2CM)



600 x 1200mm
PANNAT612 (in/out)
PANNAT612L (linear in/out)

398 x 600mm Coping Paver
PANNAT46-20L (textured 2CM)

300 x 600mm
PANNAT36 (in/out)

JAPAN CERAMICS





600 x 600mm
PANGR60 (in/out)
PANGR60-20 (textured 2CM)



600 x 1200mm
PANGR612 (in/out)
PANGR612L (linear in/out)



398 x 600mm Coping Paver
PANGR46-20L (textured 2CM)



300 x 600mm
PANGR36 (in/out)



JAPAN CERAMICS

Technical Specifications

Properties	Test Method	Required Value	Value	Applies to
Water absorption	ASTM C373	⩽ 0.5%	⩽ 0.11%	Full range
Determination of dimensions	N/A	N/A	N/A	Full range
Breaking strength	ASTM C648	⩾ 1100 N	⩾ 2143 N	Full range
Abrasion resistance	ASTM C1027	As reported	Class 3	Full range
Slip resistance (wet pendulum test)	AS 4586:2013	N/A	P4 - In/Out P5 - Textured	In/Out Textured
Slip resistance (oil wet ramp test)	AS 4586:2013	N/A	R10	In/Out Textured
Chemical resistance	ASTM C650	As reported	Class A	Full range
Stain resistance	ASTM C1378	As reported	Class A	Full range
Origin	N/A	N/A	China	Full range
Shade variation	N/A	N/A	V2	Full range



JAPAN CERAMICS

Packing Information

Tile Description		Quantity per Box	Quantity per m2		Quantity per Pallet	
Size (mm)	Finish	Pieces	Pieces	Weight	m2	Boxes
300 x 600	In/Out	8	5.56	22.00kg	57.60	40
600 x 600	In/Out	4	2.78	22.00kg	57.60	40
600 x 600 2CM Paver	Textured	2	2.78	45.00kg	28.80	40
600 x 1200	In/Out	2	1.39	22.00kg	40.32	28
398 x 600 2CM Paver	Textured	3	3	11.50kg	25.92	36



The data and information contained in these specification sheets are indicative only unless stated otherwise. As Japan Ceramics cannot control the conditions under which these products are manufactured, the specifications supplied should be considered as suggested guidelines only and are subject to batch variation. The information contained in these specification sheets should not be considered a warranty, expressed or implied, including, but not limited to, a warranty of merchantability or fitness for a particular purpose. To the maximum extent permitted by law, ColorTile will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given in respect of any specification provided herein other than those that cannot be excluded under the Australian Consumer Law.

JAPAN CERAMICS

IMPORTANT NOTE:
Slip ratings are indicative only. Actual performance may vary depending on installation, surface conditions, and maintenance.

Slip Check to AS 4586-2013

Panama

Report Number: R34074b
Report Date: 7 July 2025
Total Number of Pages 2

Safe Environments quality management system is certified to ISO 9001:2015

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Limited

Issued by

Safe Environments Pty Limited
6/7 Inglewood Place
Norwest NSW 2153

Prepared for

Japan Ceramics Pty Ltd
26 Daisy Street
Revesby NSW 2212

Approved by

Ratan Venkatesan
Authorised Signatory

SlipCheck
CREATING SAFE ENVIRONMENTS
www.FloorSlipTest.com.au

6/7 Inglewood Place
Norwest NSW 2153
Phone02 9621 3706
info@SafeEnvironments.com.au

7 July 2025

Test Report No. R34074b

Slip ResistanceClassificationofNewPedestrianSurface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by:	Japan Ceramics Pty Ltd
Client Address:	26 Daisy Street Revesby NSW 2212
Product Manufacturer:	Max Glory
Product Description:	Panama
Test conducted according to:	AS 4586:2013 Appendix A
Sampling Procedures:	Performed by client and tested as received.
Location:	6/7 Inglewood Place, Norwest NSW 2153
Conducted by:	Ratan Venkatesan
Date:	07 July 2025
Sample:	Unfixed
Rubber slider used:	Slider 96
Slope of specimen:	Tested on a flat level surface
Direction of Test:	N/A
Temperature:	17°C
Cleaning:	None
Conditioned:	Grade P 400 paper dry followed by wet lapping film

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	51	50	50	55	45

Reported SRV of Sample:	**50**
Class:	**P4**

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8%, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.

This test report shall not be reproduced unless in full, without written approval of Safe EnvironmentsPtyLtd

SafeEnvironments
MANAGING PROPERTY RISK

ilac-MRA NATA
Accreditation No. 17139

IMPORTANT NOTE:
Slip ratings are indicative only. Actual performance may vary depending on installation, surface conditions, and maintenance.

Slip Check to AS 4586-2013

Panama/Portofino 20mm Paver

Report Number: R36227
Report Date: 15 September 2026
Total Number of Pages 2

Safe Environments quality management system is certified to ISO 9001:2015

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Limited

Issued by

Safe Environments Pty Limited
6/7 Inglewood Place
Norwest NSW 2153

Prepared for

Japan Ceramics Pty Ltd
26 Daisy Street
Revesby NSW 2212

Approved by

Carl Strautins
Authorised Signatory

SlipCheck
CREATING SAFE ENVIRONMENTS
www.FloorSlipTest.com.au

6/7 Inglewood Place
Norwest NSW 2153
Phone02 9621 3706
info@SafeEnvironments.com.au

15 September 2026

Test Report No. R36227

Slip Resistance ClassificationofNewPedestrianSurface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by:	Japan Ceramics Pty Ltd
Client Address:	26 Daisy Street Revesby NSW 2212
Product Manufacturer:	Max Glory
Product Description:	Panama/Portofino 20mm Paver
Test conducted according to:	AS 4586:2013 Appendix A
Sampling Procedures:	Performed by client and tested as received.
Location:	6/7 Inglewood Place, Norwest NSW 2153
Conducted by:	Nathan Phanith

Date:	15 September 2026	Temperature:	22°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	N/A		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	58	59	57	60	61

Reported SRV of Sample:	**59**
Class:	**P5**

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8%, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.

This test report shall not be reproduced unless in full, without written approval of Safe EnvironmentsPtyLtd