Riverwood



JAPAN CERAMICS

26 Daisy Street
Revesby NSW 2212
P 02 9772 2088
E sales@japanceramics.com.au
japanceramics.com.au

RIVERWOOD

JAPAN CERAMICS
26 Daisy Street
Revesby NSW 2212
P 02 9772 2088
E sales@japanceramics.com.au
japanceramics.com.au

COLOURS, FORMATS & FINISHES

In/Out | P4	Limed	Fossil	Pure	Vintage	Eiger	Mocca
200 x 1200mm	●	●	●	●	●	●

FINISH: **IN**/**OUT** | CATEGORY: PORCELAIN TILES | EDGE DETAIL: RECTIFIED | V RATING: V2



Colour variation is an inherent property of all kiln-fired products. Tiles supplied may vary from samples provided. All slip ratings are provided subject to the guidelines outlined in our terms and conditions.

© JAPAN CERAMICS





200 x 1200mm
RIVWLIM120 (in/out)





200 x 1200mm
RIVWFOS120 (in/out)

JAPAN CERAMICS





200 x 1200mm
RIVWPUR120 (in/out)





200 x 1200mm
RIVWVIN120 (in/out)

JAPAN CERAMICS





200 x 1200mm
RIVWEIG120 (in/out)





200 x 1200mm
RIVWMOC120 (in/out)

JAPAN CERAMICS

Technical Specification

Properties	Test Method	Required Value	Value	Applies to
Water absorption	EN ISO 105433:2018	⩽ 0.5%	⩽ 0.5%	Full range
Breaking strength	EN ISO 105454:2019	⩾ 1300N	⩾ 1300N	Full range
Modulus of rupture	EN ISO 105454:2019	⩾ 35 N/mm2	⩾ 35 N/mm2	Full range
Slip resistance (wet pendulum test)	AS 4586-2013/Amdt 12017 Appendix A	N/A	P4 - In/Out	In/Out
Chemical resistance	EN ISO 1054513:2016	MINIMUM B	Pass	Full range
Stain resistance	AS 4459.14-1999	Min class 3	Pass	Full range
Origin	N/A	N/A	China	Full range
Shade variation	N/A	N/A	V2	Full range



JAPAN CERAMICS

Packing Information

Tile Description		Quantity per Box	Quantity per m2		Quantity per Pallet	
Size (mm)	Finish	Pieces	Pieces	Weight	m2	Boxes
200 x 1200 - Eiger, Limed, Mocca, Pure Vintage	In/Out	5	4.17	24.58kg	45.60	38
200 x 1200 - Fossil	In/Out	6	4.17	24.58kg	69.12	48



The data and information contained in these specification sheets are indicative only unless stated otherwise. As Japan Ceramics cannot control the conditions under which these products are manufactured, the specifications supplied should be considered as suggested guidelines only and are subject to batch variation. The information contained in these specification sheets should not be considered a warranty, expressed or implied, including, but not limited to, a warranty of merchantability or fitness for a particular purpose. To the maximum extent permitted by law, ColorTile will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given in respect of any specification provided herein other than those that cannot be excluded under the Australian Consumer Law.

JAPAN CERAMICS

IMPORTANT NOTE:
Slip ratings are indicative only. Actual performance may vary depending on installation, surface conditions, and maintenance.

Slip Check to AS 4586-2013

Riverwood

Report Number: R33536a
Report Date: 28 March 2025
Total Number of Pages 2

Safe Environments quality management system is certified to ISO 9001:2015

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Limited

Issued by

Safe Environments Pty Limited
6/7 Inglewood Place
Norwest NSW 2153

Prepared for

Japan Ceramics Pty Ltd
26 Daisy Street
Revesby NSW 2212

Approved by

Ratan Venkatesan
Authorised Signatory

info@SafeEnvironments.com.au
www.SafeEnvironments.com.au

SlipCheck
CREATING SAFE ENVIRONMENTS
www.FloorSlipTest.com.au

6/7 Inglewood Place
Norwest NSW 2153
Phone02 9621 3706
info@SafeEnvironments.com.au

28 March 2025

Test Report No. R33536a

Slip ResistanceClassificationofNewPedestrianSurface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by:	Japan Ceramics Pty Ltd
Client Address:	26 Daisy Street Revesby NSW 2212
Product Manufacturer:	Padua Ceramics
Product Description:	Riverwood
Test conducted according to:	AS 4586:2013 Appendix A
Sampling Procedures:	Performed by client and tested as received.
Location:	6/7 Inglewood Place, Norwest NSW 2153
Conducted by:	Mathew Sutton
Date:	28 March 2025
Sample:	Unfixed
Rubber slider used:	Slider 96
Slope of specimen:	Tested on a flat level surface
Direction of Test:	Parallel to wood grain pattern
Temperature:	27°C
Cleaning:	None
Conditioned:	Grade P 400 paper dry followed by wet lapping film

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	45	45	44	46	47

Reported SRV of Sample:	**45**
Class:	**P4**

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8%, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.

This test report shall not be reproduced unless in full, without written approval of Safe EnvironmentsPtyLtd