# Sella



JAPAN CERAMICS


26 Daisy Street
Revesby NSW 2212
P 02 9772 2088
E sales@japanceramics.com.au
japanceramics.com.au

# SELLA

JAPAN CERAMICS
26 Daisy Street
Revesby NSW 2212
P 02 9772 2088
E sales@japanceramics.com.au
japanceramics.com.au

## COLOURS, FORMATS & FINISHES





| **Textured \| P5** | White | Natural | Grey |
|---|---|---|---|
| 440 x 660mm Flagstone | ● | ● | ● |

FINISH: **TEXTURED** | CATEGORY: PORCELAIN TILES | EDGE DETAIL: UNRECTIFIED | V RATING: V2








440 x 660mm
SELWH46 (textured)






440 x 660mm
SELNA46 (textured)

JAPAN CERAMICS






440 x 660mm
SELGY46 (textured)



JAPAN CERAMICS

# Technical Specifications

| Properties | Test Method | Required Value | Value | Applies to |
|---|---|---|---|---|
| Water absorption | ISO 10545-3 | ⩽ 0.5% | ⩽ 0.10% | Full range |
| Determination of dimensions | ISO 10545-2 | Length and width 0.6% Thickness 0.5% Edge straightness 0.5% Surface flatness 0.5% | Complies with standards | Full range |
| Breaking strength | ISO 10545-4 | ⩾ 1300 N | Complies with standards | Full range |
| Abrasion resistance | ISO 10545-6 | Max 175mm3 | Complies with standards | Full range |
| Slip resistance (wet pendulum test) | Wet Pendulum Test | N/A | P5 | Textured |
| Slip resistance (oil wet ramp test) | DIN 51130 | N/A | R12 | Full range |
| Chemical resistance | ISO 10545-13 | Minimum UB | Complies with standards | Full range |
| Stain resistance | N/A | N/A | N/A | Full range |
| Origin | N/A | N/A | Spain | Full range |
| Shade variation | N/A | N/A | V3 | Full range |



JAPAN CERAMICS

# Packing Information

| Tile Description | | Quantity per Box | Quantity per m2 | | Quantity per Pallet | |
|---|---|---|---|---|---|---|
| Size (mm) | Finish | Pieces | Pieces | Weight | m2 | Boxes |
| 440 x 660 Flagstone | Textured | 4 | 3.42 | 24.00kg | 56.16 | 48 |



*The data and information contained in these specification sheets are indicative only unless stated otherwise. As Japan Ceramics cannot control the conditions under which these products are manufactured, the specifications supplied should be considered as suggested guidelines only and are subject to batch variation. The information contained in these specification sheets should not be considered a warranty, expressed or implied, including, but not limited to, a warranty of merchantability or fitness for a particular purpose. To the maximum extent permitted by law, ColorTile will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given in respect of any specification provided herein other than those that cannot be excluded under the Australian Consumer Law.*

JAPAN CERAMICS

**IMPORTANT NOTE:**
**Slip ratings are indicative only. Actual performance may vary depending on installation, surface conditions, and maintenance.**

# Slip Check to AS 4586-2013

# Sella Flagstone

**Report Number: R28746b**
**Report Date: 15 May 2023**
**Total Number of Pages 2**

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Limited

| Issued by | Prepared for | Approved by |
|---|---|---|
| Safe Environments Pty Limited<br>Unit 4, 40 Bessemer Street<br>Blacktown NSW 2148 | Japan Ceramics<br>26 Daisy Street<br>Revesby NSW 2212 | Dylan Anderson<br>Authorised Signatory |

SlipCheck
CREATING SAFE ENVIRONMENTS
www.FloorSlipTest.com.au

Unit 4/40 Bessemer St
Blacktown NSW 2148
Phone 02 9621 3706
info@SafeEnvironments.com.au

15 May 2023

# Test Report No. R28746b

## Slip ResistanceClassificationofNewPedestrianSurface Materials

**AS 4586-2013 Appendix A (Wet Pendulum Test)**

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

| | |
|---|---|
| Requested by: | Japan Ceramics |
| Client Address: | 26 Daisy Street<br>Revesby NSW 2212 |
| Product Manufacturer: | Realonda Ceramica |
| Product Description: | Sella Flagstone |
| Test conducted according to: | AS 4586:2013 Appendix A |
| Sampling Procedures: | Performed by client and tested as received. |
| Location: | 4/40 Bessemer Street, Blacktown NSW 2148 |
| Conducted by: | Yuliana Vargolomova |

| | | | |
|---|---|---|---|
| Date: | 11 May 2023 | Temperature: | 18 C |
| Sample: | Unfixed | Cleaning: | None |
| Rubber slider used: | Slider 96 | Conditioned: | Grade P 400 paper dry followed by wet lapping film |
| Slope of specimen: | Tested on a flat level surface | | |
| Direction of Test: | NA | | |

| | Specimen 1 | Specimen 2 | Specimen 3 | Specimen 4 | Specimen 5 |
|---|---|---|---|---|---|
| Mean BPN of last 3 swings: | 70 | 64 | 72 | 74 | 66 |

| | |
|---|---|
| **Reported SRV of Sample:** | **69** |
| **Class:** | **P5** |

The expanded uncertainty ($U_{95}$) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8 %, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.

This test report shall not be reproduced unless in full, without written approval of Safe EnvironmentsPtyLtd