Venistone



JAPAN CERAMICS

26 Daisy Street
Revesby NSW 2212
P 02 9772 2088
E sales@japanceramics.com.au
japanceramics.com.au

VENISTONE

COLOURS, FORMATS & FINISHES

In/Out | P4	White	Cream	Light Grey	Dark Grey	Charcoal
600 x 1200mm	●	●	●	●	●
600 x 600mm	●	●	●	●	●
600 x 600m	●	●	●	●	●
300 x 600mm	●	●	●	●	●
300 x 300mm	●	●	●	●	●

Textured | P5

600 x 600mm	●	●	●	●	●

FINISH: **IN/OUT** | CATEGORY: PORCELAIN TILES | EDGE DETAIL: RECTIFIED | V RATING: V3
FINISH: **TEXTURED** | CATEGORY: PORCELAIN TILES | EDGE DETAIL: RECTIFIED | V RATING: V3







600 x 600mm
VEISTWH60 (in/out)
VEISTWH60-20 (textured 2CM)



600 x 1200mm
VEISTWH612 (in/out)



300 x 300mm
VEISTWH30 (in/out)



300 x 600mm
VEISTWH36 (in/out)





600 x 600mm
VEISTCR60 (in/out)
VEISTCR60-20 (textured 2CM)



600 x 1200mm
VEISTCR612 (in/out)



300 x 300mm
VEISTCR30 (in/out)



300 x 600mm
VEISTCR36 (in/out)

JAPAN CERAMICS





600 x 600mm
VEISTLG60 (in/out)
VEISTLG60-20 (textured 2CM)




600 x 1200mm
VEISTLG612 (in/out)




300 x 300mm
VEISTLG30 (in/out)



300 x 600mm
VEISTLG36 (in/out)





600 x 600mm
VEISTDG60 (in/out)
VEISTDG60-20 (textured 2CM)



600 x 1200mm
VEISTDG612 (in/out)




300 x 300mm
VEISTDG30 (in/out)



300 x 600mm
VEISTDG36 (in/out)

JAPAN CERAMICS





600 x 600mm
VEISTCH60 (in/out)
VEISTCH60-20 (textured 2CM)



600 x 1200mm
VEISTCH612 (in/out)



300 x 300mm
VEISTCH30 (in/out)



300 x 600mm
VEISTCH36 (in/out)



JAPAN CERAMICS

Technical Specifications

Properties	Test Method	Required Value	Value	Applies to
Water absorption	EN ISO 10545-3	⩽ 0.5%	⩽ 0.5%	Full range
Determination of dimensions	EN ISO 10545-2	Length and width ± 0.6% Thickness ± 5.00% Transmutation ± 0.5%	Length and width ± 0.1% Thickness ± 3% Transmutation ± 0.2%	Full range
Breaking strength	EN ISO 10545-4	⩾ 1300 N	⩾ 1300 N	Full range
Modulus of rupture	EN ISO 10545-4	⩾ 35 N/mm2	⩾ 35 N/mm2	Full range
Abrasion resistance	EN ISO 10545-7	⩽ 205mm2	⩽ 160mm2	Full range
Slip resistance (wet pendulum test)	AS 4586:2013	N/A	P4	Full range
Chemical resistance	EN ISO 10545-13	Min. GB	Pass	Full range
Stain resistance	ISO 10545-14	Min class 3	Pass	Full range
Origin	N/A	N/A	China	Full range
Shade variation	N/A	N/A	V2	Full range



JAPAN CERAMICS

Packing Information

Tile Description		Quantity per Box	Quantity per m2		Quantity per Pallet	
Size (mm)	Finish	Pieces	Pieces	Weight	m2	Boxes
300 x 300	In/Out	11	11.11	22.22	53.46	54
300 x 600	In/Out	8	5.56	21.52	57.60	40
600 x 600	In/Out	4	2.78	21.52	57.60	40
600 x 600 2CM Paver	Textured	2	2.78	46.53	28.80	40
600 x 1200	In/Out	2	1.39	23.26	40.32	28



The data and information contained in these specification sheets are indicative only unless stated otherwise. As Japan Ceramics cannot control the conditions under which these products are manufactured, the specifications supplied should be considered as suggested guidelines only and are subject to batch variation. The information contained in these specification sheets should not be considered a warranty, expressed or implied, including, but not limited to, a warranty of merchantability or fitness for a particular purpose. To the maximum extent permitted by law, ColorTile will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given in respect of any specification provided herein other than those that cannot be excluded under the Australian Consumer Law.

JAPAN CERAMICS

IMPORTANT NOTE:
Slip ratings are indicative only. Actual performance may vary depending on installation, surface conditions, and maintenance.

Slip Check to AS 4586-2013

Venistone In/Out

Report Number: R32007
Report Date: 3 September 2024
Total Number of Pages 2

Safe Environments quality management system is certified to ISO 9001:2015

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

This test report shall not be reproduced unless in full, without written approval of Safe Environments Pty Limited

Issued by

Safe Environments Pty Limited
6/7 Inglewood Place
Norwest NSW 2153

Prepared for

Japan Ceramics
26 Daisy Street
Revesby NSW 2212

Approved by

Ratan Venkatesan
Authorised Signatory

SlipCheck
CREATING SAFE ENVIRONMENTS
www.FloorSlipTest.com.au

6/7 Inglewood Place
Norwest NSW 2153
Phone02 9621 3706
info@SafeEnvironments.com.au

3 September 2024

Test Report No. R32007

Slip Resistance ClassificationofNewPedestrianSurface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by:	Japan Ceramics
Client Address:	26 Daisy Street Revesby NSW 2212
Product Manufacturer:	Foshan Padua
Product Description:	Venistone In/Out
Test conducted according to:	AS 4586:2013 Appendix A
Sampling Procedures:	Performed by client and tested as received.
Location:	6/7 Inglewood Place, Norwest NSW 2153
Conducted by:	Danish Raza
Date:	03 September 2024
Sample:	Unfixed
Rubber slider used:	Slider 96
Slope of specimen:	Tested on a flat level surface
Direction of Test:	N/A
Temperature:	20 C
Cleaning:	None
Conditioned:	Grade P 400 paper dry followed by wet lapping film

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	52	54	47	48	50

Reported SRV of Sample:	**50**
Class:	**P4**

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8%, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.

This test report shall not be reproduced unless in full, without written approval of Safe EnvironmentsPtyLtd